



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification: <b>C09J 7/02, B32B 27/32, C08J 5/18</b>	<b>A1</b>	(11) International Publication Number: <b>WO 00/29499</b> (43) International Publication Date: <b>25 May 2000 (25.05.2000)</b>
--	-----------	---

(21) International Application Number: PCT/US98/24105

(22) International Filing Date: 12 November 1998 (12.11.1998)

Published

## (60) Parent Application or Grant

MINNESOTA MINING AND MANUFACTURING  
COMPANY [/]; (). PEARSON, Scott, D. [/]; (). HAGER,  
Patrick, J. [/]; (). PEARSON, Scott, D. [/]; (). HAGER, Patrick,  
J. [/]; (). TRUSSELL, James, J.; ().

(54) Title: ORIENTED POLYPROPYLENE FILMS FOR ADHESIVE TAPE

(54) Titre: FILMS DE POLYPROPYLENE ORIENTE POUR RUBAN ADHESIF

## (57) Abstract

An adhesive tape (10) comprising a backing (11) and a layer of adhesive (18) on the backing. The backing comprises a biaxially oriented substrate which comprises an isotactic polypropylene composition. The tapes and backings of this invention can be severed readily using commercial tape dispensers having metal or plastic cutting teeth to produce cleanly serrated cut edges on the tape. The biaxially oriented substrate is preferably made from a resin comprising an isotactic polypropylene homopolymer having a melt flow rate greater than 8 grams/10 minutes, more preferably greater than 12 grams/10 minutes, and still more preferably greater than about 20 grams/10 minutes. One preferred way to obtain such a resin is to blend: A) at least one isotactic polypropylene homopolymer "A" having a weight average molecular weight of at least 350,000 grams/mole and melt a flow rate of about 0.5-8 grams/10 minutes, more preferably about 0.5-5 grams/10 minutes; with B) at least one isotactic polypropylene homopolymer "B" having a weight average molecular weight of at least 100,000 grams/mole and a melt flow rate greater than 8 grams/10 minutes, and preferably greater than about 20 grams/10 minutes, and more preferably greater than about 50 grams/10 minutes.

## (57) Abrégé

L'invention se rapporte à un ruban adhésif (10) comportant un support (11) recouvert d'une couche d'adhésif (18). Ledit support comporte un substrat à orientation biaxiale qui comporte une composition de polypropylène isostatique. Les rubans et les supports de cette invention peuvent être facilement coupés au moyen de distributeurs de ruban du commerce qui sont pourvus de dents coupantes en matière plastique ou en métal qui permettent de former des bords dentés, coupés correctement, sur le ruban. Le substrat à orientation biaxiale est de préférence constitué d'une résine comportant un homopolymère de polypropylène isostatique présentant un coefficient d'écoulement à l'état fondu supérieur à 8 grammes/10 minutes, de préférence supérieur à 12 grammes/10 minutes, et idéalement supérieur à 20 grammes/10 minutes. De préférence, on produit cette résine en mélangeant (A) au moins un homopolymère de polypropylène isostatique "A" ayant un poids moléculaire moyen d'au moins 350 000 grammes/mole et un coefficient d'écoulement à l'état fondu compris entre 0,5 et 8 grammes/10 minutes, de préférence compris entre 0,5 et 5 grammes/10 minutes, et (B) au moins un homopolymère de polypropylène isostatique "B" ayant un poids moléculaire moyen d'au moins 100 000 grammes/mole et un coefficient d'écoulement à l'état fondu compris supérieur à 8 grammes/10 minutes, de préférence supérieur à 20 grammes/10 minutes et idéalement supérieur à 50 grammes/10 minutes.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>6</sup> : C09J 7/02, C08J 5/18, B32B 27/32</p>	<p>A1</p>	<p>(11) International Publication Number: <b>WO 00/29499</b> (43) International Publication Date: 25 May 2000 (25.05.00)</p>
<p>(21) International Application Number: PCT/US98/24105 (22) International Filing Date: 12 November 1998 (12.11.98) (71) Applicant (for all designated States except US): MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventors; and (73) Inventors/Applicants (for US only): PEARSON, Scott, D. [US/US]; 1141 Saddlebrook Lane, Woodbury, MN 55125 (US). HAGER, Patrick, J. [US/US]; 5877 Fawn Trail Circle, Woodbury, MN 55129 (US). (74) Agents: TRUSSELL, James, J. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  Published With international search report.</p>
<p>(54) Title: ORIENTED POLYPROPYLENE FILMS FOR ADHESIVE TAPE</p> <p>(57) Abstract</p> <p>An adhesive tape (10) comprising a backing (11) and a layer of adhesive (18) on the backing. The backing comprises a biaxially oriented substrate which comprises an isotactic polypropylene composition. The tapes and backings of this invention can be severed readily using commercial tape dispensers having metal or plastic cutting teeth to produce cleanly serrated cut edges on the tape. The biaxially oriented substrate is preferably made from a resin comprising an isotactic polypropylene homopolymer having a melt flow rate greater than 8 grams/10 minutes, more preferably greater than 12 grams/10 minutes, and still more preferably greater than about 20 grams/10 minutes. One preferred way to obtain such a resin is to blend: A) at least one isotactic polypropylene homopolymer "A" having a weight average molecular weight of at least 350,000 grams/mole and melt a flow rate of about 0.5-8 grams/10 minutes, more preferably about 0.5-5 grams/10 minutes; with B) at least one isotactic polypropylene homopolymer "B" having a weight average molecular weight of at least 100,000 grams/mole and a melt flow rate greater than 8 grams/10 minutes, and preferably greater than about 20 grams/10 minutes, and more preferably greater than about 50 grams/10 minutes.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**Description**

5

10

15

20

25

30

35

40

45

50

55

## Oriented Polypropylene Films for Adhesive Tape

### TECHNICAL FIELD

The present invention generally relates to biaxially oriented films made from polypropylene and tapes comprising such films.

### BACKGROUND OF THE INVENTION

Commercially available pressure sensitive adhesive tapes are usually provided in a roll form on a tape dispenser (see e.g. U.S. Patent Nos. 4,451,533 and 4,908,278). Tape dispensers typically have either a metal or plastic serrated cutting blade. "Severability" of adhesive tape is defined as the ability to cut or sever a length of tape by pulling the tape over the teeth on the serrated cutting edge of a tape dispenser with a desired amount of energy or work. Severability is also referred to as "dispensability."

It is desired that the severed tape does not chip, sliver, fracture or break in an unpredictable manner (see U.S. Patent Nos. 4,451,533 and 4,908,278). Such severability is desirable to produce a cleanly serrated cut edge on the severed tape strip. Severability is governed primarily by the mechanical properties of the backing of the adhesive tape. Cleanly serrated edges are preferred for aesthetic reasons in applications such as gift wrapping, mending, and the like. The ease with which an adhesive tape can be severed depends on the deformation and resistance to break (toughness) of the tape backing film, also referred to as the substrate. Typically, the substrate is coated or laminated with surface layers to provide an adhesive surface or a matte or writable surface. The greater the energy required to sever the film, the more extensive the resulting damage to the film will be and the less aesthetically appealing the resulting severed edge. In most cases, energy to sever of the tape is governed primarily by the substrate, with little affect by the adhesive or other layers or coatings. This is believed to be due in part to the elastic strain energy built up during the deformation being suddenly and catastrophically released when the film's inherent strength limit is surpassed. The subsequent failure propagates uncontrollably in a tearing or ripping fashion so that the cut edge does not follow closely the contour of the teeth of the dispenser. The propagation also is directed along the underlying fibril orientation distribution rather than closely following the contour of the dispenser teeth.

5 The majority of commercially available biaxially oriented polypropylene film is produced by the flat film or tenter stretching process. Typical tenter processes serve to biaxially stretch films either predominately simultaneously or predominately sequentially. Sequential tenter stretching is currently the most widely used biaxial film processing  
10 5 method. Typically, a thick sheet is extruded and rapidly quenched to form spherules having  $\alpha$ -morphology with a monoclinic unit cell. This thick sheet is then reheated to a suitable stretching temperature and stretched in a first lengthwise or longitudinal stretching step, followed by a second transverse stretching step and then the film is annealed to produce a flat film having uniform thickness. Simultaneous tenter stretched films  
15 10 comprise a minor part of the film backing market because, although such processes can continuously stretch films in both longitudinal and transverse directions, they have historically proven costly, slow, and inflexible regarding allowable drawing ratios.

Commercially available biaxially oriented polypropylene films are well known for their toughness, moisture stability, good color, slivering resistance, and clarity and have  
25 15 long been used as adhesive tape backings (see U.S. Patent Nos. 3,241,662 and 3,324,218). Such films are produced typically with so-called "film grade" isotactic polypropylene resins having high molecular weight and low melt flow rates between about 2-8 grams/10 minutes as measured using ASTM D 1238-95.

High molecular weight polyolefin resins are well known in the art to produce  
20 20 biaxially oriented film having uniform stretch and thickness, without hardbands, wrinkles or other defects. High molecular weight imparts cohesive strength to the cast sheet, allowing uniform stretching at the strain rates typical of commercial biaxial film stretching equipment, especially the high strain rates that can occur in sequential biaxial orientation film lines.

40 25 However, especially in the sequential biaxial orientation case, high molecular weight produces film having high toughness, and adhesive tapes produced from such films tend to elongate significantly before breaking while under load, which renders such tapes extremely difficult to sever, particularly on a plastic-bladed dispenser. The elongation to break for such tapes results in an undesirably large amount of work on the part of the user.

30 It is known to add other components to polypropylene resin to improve processability or improve severability for production of adhesive tape backing films.

5 Small amounts (less than about 10% by weight) of low molecular weight additives like waxes or lubricants can be employed to allow the cast web to be more easily stretched to a film by reducing the internal friction between polymer chains as they slide past each other. WO 97/46369 discloses use of a polypropylene wax additive, by which the  
10 execution of a process for preparing a biaxially stretched polypropylene film at high speeds and with high reliability will be possible.

15 Components like hydrocarbon tackifiers, high Tg polymers and the like can be added to enhance the film brittleness and thereby reduce the work required to sever the film. Such materials may prove difficult to process or impart undesirable stiffness, opacity, off-colors, and higher cost to the finished film.

20 JP 53-34834 discloses a biaxially oriented polypropylene based adhesive tape with cutting properties formed from a polymer mixture containing 20-80% of polypropylene and 80-20% of a low molecular weight polyolefin. It is further disclosed that in the case when the molecular weight of the low molecular weight polyolefin becomes greater than  
25 20,000 grams/mole, it becomes a material where the cutting properties are significantly deteriorated.

30 U.S. Pat. No. 3,887,745 discloses a finger-tearable adhesive tape with a film base comprising a layer of polypropylene polymer film which is biaxially oriented and at least one other layer of a polypropylene polymer film which is uniaxially oriented in a  
20 transverse direction, the melting point of the uniaxially oriented film being 0.5-10°C higher than the melting point of the biaxially oriented film, and the total thickness of the  
35 uniaxially oriented film being 1.2 - 5.0 times greater than the total thickness of the biaxially oriented film.

40 U.S. Pat. No. 4,393,115 discloses a laminate film having hand-cutting properties comprising a biaxially oriented polypropylene layer and a uniaxially oriented  
25 polypropylene layer oriented only in the width direction, laminated with a stretched thin surface layer of propylene-ethylene block copolymer. The thickness of the uniaxially  
45 oriented layer is in the range between about 1.2 and 5.0 times the thickness of the biaxially oriented polypropylene layer.

30 U.S. Pat. No. 4,414,261 discloses a severable polypropylene adhesive tape having a base sheet comprising an intermediate layer made of crystalline polypropylene  
50

5 containing from 25 to 35% by weight of a petroleum resin and outer layers made of a crystalline polypropylene laminated on both sides of the intermediate layer, the thickness of the intermediate layer is within a range from 60 to 90% of the base sheet.

10 U.S. Pat. No. 4,447,485 discloses an adhesive tape with finger-tearability and severability comprising a base sheet of a polypropylene resin containing from 5 to 50% by weight of a methylpentene polymer and a subsidiary layer formed on one or both sides of the main layer composed of crystalline polypropylene having a melting point of at least 15 the melting point of the methylpentene polymer, and a bonding layer of a carboxylic acid-modified polypropylene.

20 U.S. Pat. No. 5,474,820 discloses a multilayer polypropylene film comprising a base layer of polypropylene and at least one outer layer containing a mixture of HDPE and one or more olefin homopolymers, copolymers or terpolymers and the film has a silk-matte finish. The polypropylene polymer of the base layer has a melting point of at least 140° C and the melt flow index is in the range of 0.5-15 grams/10 minutes.

#### 25 15 SUMMARY OF THE INVENTION

30 The present invention provides biaxially oriented substrates comprising isotactic polypropylene compositions. Such biaxially oriented substrates are well suited for use as adhesive tape backings. The tapes and backings of this invention can be severed readily 20 using commercial tape dispensers having metal or plastic cutting teeth to produce cleanly serrated cut edges on the tape. That is, the preferred adhesive tapes and backings 35 described herein have a serrated edge that closely follows the contour of the serrated cutting teeth when tested by the Dispense Test - Metal Blade or the Dispense Test - Plastic Blade described herein.

40 25 In one aspect, the present invention provides an adhesive tape comprising a backing and a layer of adhesive on the backing. The backing comprises a biaxially oriented substrate which comprises an isotactic polypropylene composition.

45 Preferably, the biaxially oriented substrate comprises an isotactic polypropylene composition such that the backing has the following properties taken individually or in any 30 desirable combination:



5 A) an elongation to break of from 40% to 170%;

B) an energy to sever of up to 350 N-cm/cm<sup>2</sup> when severed according to  
The Dispense Test - Metal Blade;

10 C) an energy to sever of up to 700 N-cm/cm<sup>2</sup> when severed according to  
The Dispense Test - Plastic Blade; and

15 D) an elongation of up to 4% when severed according to either The  
Dispense Test - Metal Blade or The Dispense Test - Plastic Blade.

The above characteristics are defined with respect to the backing without adhesive  
present. It is expected that adhesive has little impact on the characteristics described  
20 above.

In one preferred embodiment, the biaxially oriented substrate comprises a  
polypropylene composition such that the biaxially oriented substrate has the following  
characteristics taken individually or in any desirable combination:

25 A) a weight average molecular weight of at least 100,000 grams/mole;

15 B) a melt flow rate of at least 8 grams/10 minutes, more preferably 12  
grams/10 minutes, and most preferably 20 grams/10 minutes;

30 C) a high isotacticity content greater than about 90% as measured by n-  
heptane soluble fraction of less than about 15% by weight or having at least 60%  
isotactic pentads as determined by <sup>13</sup>C-NMR analysis; and

35 D) a density preferably of about 0.86-0.92 grams/cm<sup>3</sup>, more preferably  
20 about 0.88-0.91 grams/cm<sup>3</sup>.

The biaxially oriented substrate is preferably made from a resin comprising an  
isotactic polypropylene homopolymer having a melt flow rate greater than 8 grams/10  
40 minutes, more preferably greater than 12 grams/10 minutes, and still more preferably  
greater than about 20 grams/10 minutes.  
25

45 The resin also preferably has:

A) a high isotacticity content greater than about 90% as measured by n-heptane  
soluble fraction content of less than about 15% by weight or having at least

5 60% isotactic pentads as determined by C-13 nuclear magnetic resonance (NMR) analysis;

B) a weight average molecular weight (Mw) of at least 100,000 grams/mole;

C) a density of 0.86 – 0.92 grams/cm<sup>3</sup>, preferably 0.88 - 0.91 grams/cm<sup>3</sup>; and

10 D) a melting point temperature of about 160-166° C.

One preferred way to obtain such a resin is to blend:

15 A) at least one isotactic polypropylene homopolymer "A" having a weight average molecular weight of at least 350,000 grams/mole as determined by size exclusion chromatography and melt a flow rate of about 0.5-8 grams/10 minutes, more preferably about 0.5-5 grams/10 minutes; with

20 B) at least one isotactic polypropylene homopolymer "B" having a weight average molecular weight of at least 100,000 grams/mole as determined by size exclusion chromatography and a melt flow rate greater than 8 grams/10 minutes, and preferably greater than about 20 grams/10 minutes, and more preferably greater than about 50 grams/10 minutes. The practical upper limit for the melt flow rate of Resin B may be about 350–400 grams/10 minutes, although the present invention is not so limited. The preferred upper limit is about 150 grams/10 minutes. Resin B should have a sufficiently high molecular weight to exhibit molecular chain entanglement behavior, that is to behave as a solid at ambient temperature and exhibit elasticity and melt strength.

35 Resins A and B each also preferably have:

A) a high isotacticity content greater than about 90% as measured by n-heptane soluble fraction content of less than about 15% by weight or having at least 40 60% isotactic pentads as determined by C-13 nuclear magnetic resonance (NMR) analysis;

B) a density of 0.86 – 0.92 grams/cm<sup>3</sup>, preferably 0.88 - 0.91 grams/cm<sup>3</sup>; and

45 C) a melting point temperature of about 160-166° C.

30 Resins A and B can be melt mixed together and formed into a sheet and biaxially oriented to produce an adhesive tape backing, or arranged as discrete layers in a multilayer

5 film or some combination of the two and then biaxially oriented to produce an adhesive tape backing.

10 The biaxially oriented isotactic polypropylene substrate thus formed from the resin or resins described herein has a melt flow rate greater than about 8 grams/10 minutes and preferably less than about 100 grams/10 minutes, and has improved severability on commercially available adhesive tape dispensers.

15 The melt flow rates of A and B and the relative amounts of each are selected such that the backing and the biaxially oriented substrate have the desired properties and characteristics described herein.

20 Additionally, the resin may be a blend of three or more resins that satisfy the requirements of A and B stated above.

25 When using a blend, resins A and B may be mixed together in any desirable weight combinations, preferably with Resin A present in an amount from about 5 to 80 wt%, more preferably from about 20 to 70 wt%, and with Resin B preferably present in an amount of from 20 to 95 wt%, more preferably from about 30 to 80 wt%.

In one preferred embodiment, the biaxially oriented substrate is a monolayer.

30 In another preferred embodiment, biaxially oriented substrate is of multilayer construction. In preferred multilayer biaxially oriented substrate comprises discrete layers each made from a resin meeting the requirements of Resin A or B. Additionally, layers not meeting the requirements of Resins A or B may be included either as the outermost layers or within a multilayer construction. In such a case, the composite biaxially oriented substrate preferably has at least 50% of the thickness containing at least 90% isotactic polypropylene. Stated another way, of the layers that together make up the biaxially oriented substrate, the layers comprising at least 90% isotactic polypropylene account for at least 50% of the total thickness of the biaxially oriented substrate. Preferably, the multilayer biaxially oriented substrate has a composite melt flow rate of greater than about 8 grams/10 minutes, more preferably greater than 12 grams/10 minutes, and most preferably at least 20 grams/10 minutes. The multilayer biaxially oriented substrate has a composite melt flow rate of preferably less than about 100 grams/10 minutes.

5 Furthermore, the backing comprising a multilayer biaxially oriented substrate has the desired severance energy and elongation described herein.

10 The present invention comprises the desirable adhesive tapes described herein. The present invention also comprises the preferred backings described herein. The present  
5 invention also comprises the preferred biaxially oriented substrates described herein, in which case those characteristics described with respect to the backing apply to the biaxially oriented substrate. Such preferred biaxially oriented substrates may be  
15 monolayer or multilayer, with monolayer being preferred. The present invention also comprises the preferred resins and blends described herein which may be oriented to  
10 provide the preferred biaxially oriented substrates and/or backings described herein.

20 Certain terms are used in the description and the claims that, while for the most part are well known, may require some explanation. "Area stretch ratio," as used herein, indicates the ratio of the area of a given portion of a stretched film to the area of the same  
25 portion prior to stretching. For example, in a biaxially stretched film having an area stretch ratio of 36:1, a given 1 cm<sup>2</sup> portion of unstretched film would have an area of 36  
15 cm<sup>2</sup> after stretch.

30 "Biaxially oriented," when used herein to describe a film, indicates that the film has been stretched in two different directions in the plane of the film. Typically, but not  
20 always, the two directions are perpendicular. Biaxially oriented films may be sequentially stretched, simultaneously stretched, or stretched by some combination of simultaneous and  
35 sequential stretching. "Simultaneously biaxially oriented," when used herein to describe a film, indicates that significant portions of the stretching in each of the two directions are performed simultaneously.

40 Molecular weight and molecular weight distribution affect polymer process and mechanical properties. Polymer molecular weight is typically expressed as a weight  
25 average molecular weight. Typically, the molecular weight of commercially available polyolefin resins is estimated by measuring the melt flow rate ("MFR"), which increases  
45 with decreasing molecular weight and hence melt viscosity. Commercial film grade isotactic polypropylene resins for use in biaxial orientation equipment typically have a  
30 MFR in the range from about 1-6 grams/10 minutes. At very high MFR values, biaxial

orientation of polypropylene resins becomes increasingly difficult because of a lack of melt strength at useful commercial equipment speeds during the stretching operation.

Unless specified otherwise, all values of melt flow rate of inventive resins and films described herein are provided in units of grams/10 minutes measured according to ASTM D 1238-95, Flow Rates of Thermoplastics by Extrusion Plastometer, Procedure B, Condition 230/2.16.

The molecular weight distribution is often characterized by the polydispersity index which typically is the ratio of the weight average molecular weight to the number average molecular weight. The polydispersity index affects processability of polypropylene resins and also the mechanical properties of the resultant biaxially oriented film. The polydispersity index can be determined by measuring the dynamic shear properties of the polypropylene melt (see Proceedings of the 2d World Congress of Chemical Engineering, Montreal, vol. 6, pp. 333-337 (1981)). Preferably, the films of this invention have polydispersity index values between about 2 and 8, more preferably between about 2.5 and 7.

A minimum molecular weight or chain length is required to develop strength in uncrosslinked polymers. The minimum chain length is called the critical chain entanglement molecular weight ( $M_c$ ) and defines the chain length required for the onset of chain entanglements. Chain entanglements provide topological constraints to chain motion, and allow the polymer to behave like a crosslinked network and bear stress; this ability is sometimes known as green strength or web strength. Below the  $M_c$ , uncrosslinked polymer systems have no such constraints and therefore lack elasticity and undergo chain slippage and large scale stress relaxation.

For many polymers,  $M_c$  is taken as the inflection point observed for polymers in plots of viscosity against increasing molecular weight ("*Viscoelastic Properties of Polymers*," 3<sup>rd</sup> ed., J.D. Ferry, p. 242, John Wiley & Sons, NY (1980)). For molecular weights below  $M_c$ , polymer viscosity increases with the first power of molecular weight, that is, the viscosity and molecular weight increase monotonically. With decreasing chain length below  $M_c$  the polymer behaves first like a wax and finally as a viscous liquid. Above  $M_c$ , however, the polymer behaves as a viscoelastic solid and viscosity increases with molecular weight to the 3.4 power; this much greater dependence of viscosity on

5 molecular weight is explained as the effect of entanglements in constraining chain motions and increasing viscosity. Mc can therefore be interpreted as the transition between wax behavior and polymer behavior.

10 It is often desirable to provide very clear plastic film for use in clear adhesive tapes, packaging, and other applications. The adhesive tape backings herein described in this invention exhibit good clarity and low haze. The biaxially oriented polypropylene film of the present invention displays reduced haze in transmission compared to films  
15 which do not meet the requirements of this invention. The oriented films of the present invention preferably are optically clear to the unaided eye under typical interior lighting conditions. More preferably, the films have a haze of less than 5% as measured by ASTM  
10 D1003-95.  
20

#### BRIEF DESCRIPTION OF THE DRAWINGS

25 The present invention will be further explained with reference to the appended Figures, wherein like structure is referred to by like numerals throughout the several views, and wherein:  
15

30 Figure 1 is an isometric view of a length of tape according to the present invention;

Figure 2 is a side view of a roll of adhesive tape according to the present invention;

35 Figure 3 is a side view of a roll of tape on a dispenser according to the present invention;  
20

40 Figure 4 is an isometric view of a test fixture used to test the severing characteristics of film according to the present invention;

45 Figure 5 is an isometric view of the metal dispenser blade useful in the tape dispenser of Figure 3 and the test fixture of Figure 4;

25 Figure 6 is a side view of the metal dispenser blade of Figure 5;

50 Figure 7 is a view of a plastic dispenser blade taken in direction 7-7 of Figure 3;

Figure 8 is a cross-sectional view of the dispenser blade of Figure 7 taken along line 8-8 of Figure 7;

55 Figure 9 is a top view of the dispenser blade of Figure 7 taken in direction 9-9;

Figure 10 is a side view of a portion of the apparatus of Figure 4 and the metal dispenser blade of Figure 5;

Figure 11 is a side view of a portion of the apparatus of Figure 4 and the plastic dispenser blade of Figure 8; and

Figure 12 is an illustration of a typical severance or dispense testing curve for a polypropylene tape backing of the present invention.

#### DETAILED DESCRIPTION OF THE INVENTION

Referring to Figure 1, there is shown a length of tape 10 according to one preferred embodiment of the present invention. Tape 10 comprises a film backing 11 and a layer of adhesive 18. Backing 11 includes a biaxially oriented substrate 12. The biaxially oriented substrate may be a monolayer or a multilayer film. Biaxially oriented substrate 12 includes first major surface 14 and second major surface 16. Preferably, backing 11 has a thickness in the range of about 0.002 to about 0.005 centimeters. Biaxially oriented substrate 12 is coated on first major surface 14 with a layer of adhesive 18. Adhesive 18 may be any suitable adhesive as is known in the art. Backing 11 may include an optional release or low adhesion backsize layer 20 coated on the second major surface 16 of the biaxially oriented substrate 12 as is known in the art. In one preferred embodiment, biaxially oriented substrate 12 comprises a biaxially oriented monolayer polypropylene film as described herein. Backing 12 alternatively may comprise a multilayer backing, at least one of which layers comprises a biaxially oriented polypropylene film as described herein.

Biaxially oriented substrate 12 includes those portions of the backing 11 that were biaxially oriented. Biaxially oriented substrate 12 may comprise a monolayer film or a multilayer or laminated film. Preferably, biaxially oriented substrate 12 comprises a monolayer film. Backing 11 may include optional coatings 20 that are applied to biaxially oriented substrate 12. Such coatings may comprise, for example, a low adhesive backsize coating, a coating which accepts writing or printing, a coating that provides a matte finish, or the like. Tape 10 thus comprises a backing 11 and adhesive 18. The backing 11 comprises biaxially oriented substrate 12 and optional coatings 20, if present.

5 Preferably, the biaxially oriented substrate 12 comprises an isotactic polypropylene composition such that the backing 11 has the following properties taken individually or in any desirable combination:

10 A) an elongation to break of from 40% to 170%;

5 B) an energy to sever of up to 350 N-cm/cm<sup>2</sup> when severed according to The Dispense Test - Metal Blade;

15 C) an energy to sever of up to 700 N-cm/cm<sup>2</sup> when severed according to The Dispense Test - Plastic Blade; and

20 D) an elongation of up to 4% when severed according to either The Dispense Test - Metal Blade or The Dispense Test - Plastic Blade.

The above characteristics are defined with respect to the backing 11 without adhesive 18 present. It is expected that adhesive 18 has little impact on the characteristics described above.

25 In one preferred embodiment, the biaxially oriented substrate 12 comprises a polypropylene composition such that the biaxially oriented substrate has the following characteristics taken individually or in any desirable combination:

30 A) a weight average molecular weight of at least 100,000 grams/mole;

B) a melt flow rate of at least 8 grams/10 minutes, more preferably 12 grams/10 minutes, and most preferably 20 grams/10 minutes;

35 20 C) a high isotacticity content greater than about 90% as measured by n-heptane soluble fraction of less than about 15% by weight or having at least 60% isotactic pentads as determined by <sup>13</sup>C-NMR analysis; and

40 D) a density preferably of about 0.86-0.92 grams/cm<sup>3</sup>, more preferably about 0.88-0.91 grams/cm<sup>3</sup>.

25 The biaxially oriented substrate 12 is preferably made from a resin comprising an isotactic polypropylene homopolymer having a melt flow rate greater than 8 grams/10 minutes, more preferably greater than 12 grams/10 minutes, and still more preferably greater than about 20 grams/10 minutes.

50 The resin also preferably has:



5 A) a high isotacticity content greater than about 90% as measured by n-heptane soluble fraction content of less than about 15% by weight or having at least 60% isotactic pentads as determined by C-13 nuclear magnetic resonance (NMR) analysis;

10 5 B) a weight average molecular weight (Mw) of at least 100,000 grams/mole;  
C) a density of 0.86 – 0.92 grams/cm<sup>3</sup>, preferably 0.88 - 0.91 grams/cm<sup>3</sup>; and  
D) a melting point temperature of about 160-166° C.

15 One preferred way to obtain such a resin is to blend:

A) at least one isotactic polypropylene homopolymer "A" having a weight average  
10 molecular weight of at least 350,000 grams/mole as determined by size exclusion chromatography and melt a flow rate of about 0.5-8 grams/10 minutes, more preferably about 0.5-5 grams/10 minutes; with

20 B) at least one isotactic polypropylene homopolymer "B" having a weight average molecular weight of at least 100,000 grams/mole as determined by size exclusion chromatography and a melt flow rate greater than 8 grams/10 minutes, and preferably greater than about 20 grams/10 minutes, and more preferably greater than about 50 grams/10 minutes. The practical upper  
25 limit for the melt flow rate of Resin B may be about 350–400 grams/10 minutes, although the present invention is not so limited. The preferred upper limit is about 150 grams/10 minutes. Resin B should have a  
30 sufficiently high molecular weight to exhibit molecular chain entanglement behavior, that is to behave as a solid at ambient temperature and exhibit elasticity and melt strength.

35 Resins A and B each also preferably have:

40 25 A) a high isotacticity content greater than about 90% as measured by n-heptane soluble fraction content of less than about 15% by weight or having at least 60% isotactic pentads as determined by C-13 nuclear magnetic resonance (NMR) analysis;

45 B) a density of 0.86 – 0.92 grams/cm<sup>3</sup>, preferably 0.88 - 0.91 grams/cm<sup>3</sup>; and  
30 C) a melting point temperature of about 160-166° C.

5 Resins A and B can be melt mixed together and formed into a sheet and biaxially oriented to produce an adhesive tape backing, or arranged as discrete layers in a multilayer film or some combination of the two and then biaxially oriented to produce an adhesive tape backing.

10 The biaxially oriented isotactic polypropylene substrate 12 thus formed from the resin or resins described herein has a melt flow rate greater than about 8 grams/10 minutes and preferably less than about 100 grams/10 minutes, and has improved severability on commercially available adhesive tape dispensers.

15 The melt flow rates of A and B and the relative amounts of each are selected such that the backing and the biaxially oriented substrate have the desired properties and characteristics described herein.

20 Additionally, the resin may be a blend of three or more resins that satisfy the requirements of A and B stated above.

25 When using a blend, resins A and B may be mixed together by any of the well known plasticating shear mixing equipment such as extrusion mixing in any desirable weight combinations, preferably with Resin A present in an amount from about 5 to 80 wt%, more preferably from about 20 to 70 wt%, and with Resin B preferably present in an amount of from 20 to 95 wt%, more preferably from about 30 to 80 wt%. At weight compositions with Resin B in excess of about 80% the material may become difficult to process, however, the actual limit in composition is determined by the particular process and equipment employed and therefore depends on strain rate during stretching, temperature profiles, magnitude of stretching and the like.

30 When using a blend, the resin blends may be prepared by any known mixing operation, but preferably are prepared by extrusion mixing of dry components prior to film stretching or separately to produce pellets for later use.

35 Although processability may be simplified by biaxially orienting a single layer to produce film, this invention is not so limited. A plurality of layers may be incorporated in the biaxially oriented substrate 12. For example, rather than blending resins A and B and extruding a monolayer film, a multilayer film may be laminated or coextruded comprising discrete layers each made from a resin meeting the requirements of Resin A or B.

5 Additionally, layers not meeting the requirements of Resins A or B may be included either  
as the outermost layers or within a multilayer construction. In such a case, the composite  
biaxially oriented substrate 12 has at least 50% of the thickness containing at least 90%  
isotactic polypropylene. Stated another way, of the layers that together make up the  
10 5 biaxially oriented substrate 12, the layers comprising at least 90% isotactic polypropylene  
account for at least 50% of the total thickness of the biaxially oriented substrate 12.  
Additionally, the multilayer biaxially oriented substrate 12 has a composite melt flow rate  
of greater than about 8 grams/10 minutes, more preferably greater than 12 grams/10  
15 minutes, and most preferably at least 20 grams/10 minutes. The multilayer biaxially  
oriented substrate 12 has a composite melt flow rate of preferably less than about 100  
grams/10 minutes. Furthermore, the backing 11 has the desired severance energy and  
20 elongation described herein.

Further, it is anticipated that resins, or blends of two or more resins, at least one of  
which initially have a melt flow rate below 8 grams/10 minutes, could be used if the  
25 15 polypropylene is subsequently degraded or oxidized to MFR values of about 8 grams/10  
minutes or higher, preferably up to 150 grams/10 minutes.

It is well known that, in film processing, edge trim is often recycled to the  
extrusion process, either with or without repelletizing. In this regard, if the edge trim is  
30 below 8 MFR it may be considered as additional Resin A as described above and if it is  
above 8 MFR it may be considered as additional Resin B as described above. Preferably,  
edge trim would be above 8 MFR and below 150 MFR and considered as additional Resin  
35 B.

The polydispersity index is preferred to be between about 2 and 8, more preferably  
between about 2.5 and 7.5 as measured according to ASTM D 4065-95. Typically, low  
40 25 polydispersity index polypropylene resins are difficult to process on commercial biaxial  
orientation equipment, although it is anticipated that using such resins may reduce the  
severing energy of the biaxially oriented substrate. A high polydispersity index or broad  
molecular weight distribution resin may be easier to process, but is anticipated to promote  
45 higher severing energy. Thus, a balancing of molecular weight or MFR and the molecular  
weight distribution may be desirable in application of the present invention  
30

5           The compositions meeting the characteristics described herein are preferably homopolymers. When the resins are referred to herein, including the claims, as a homopolymer, this also includes resins having therein co-polymer in an amount small  
10 enough that the desired characteristics and properties of the resin and film are still met.

5           In film processing, polymer resins are subjected to high shearing stresses at high temperature. In a typical industrial extrusion system, polypropylene molecular weight degrades somewhat due to chain scission. During processing, the longest polymer  
15 molecules are degraded to a larger degree than the shorter molecules. Therefore, for a given resin the film molecular weight may be lower than the resin molecular weight.

10           The polypropylene composition can be cast into sheet form as is known in the art, to prepare a sheet suitable for stretching to arrive at the preferred biaxially oriented substrate 12 described herein. One suitable method to cast a sheet is to feed the resin into the feed hopper of a 4.45 cm single screw extruder manufactured by H.P.M. (of Mt.  
20 Gilead, OH) having an extruder barrel temperature adjusted to produce a stable  
25 homogeneous melt. The polypropylene melt can be extruded through a 17.8 cm single manifold sheet die onto a rotating water cooled steel casting wheel having 50-60° C water circulating through it. The cast sheet can be quenched by passing through a water bath maintained at about 30°C to produce a cast sheet having a thickness of about 0.12-0.16  
30 cm.

20           The sheet is then biaxially oriented to provide biaxially oriented substrate 12 having the desired characteristics and properties described herein.  
35

          The preferred properties described herein may be obtained by any suitable method and apparatus for biaxially orienting the biaxially oriented substrate 12. Of all stretching  
40 methods, the methods most preferred for commercial manufacture of films for tape  
25 backings include biaxial stretching by mechanical tenter such as the methods and apparatus disclosed in U.S. Patent Nos. 4,330,499 and 4,595,738, and more preferably by the methods and tenter apparatus for simultaneous biaxial stretch disclosed in U.S. Patent  
45 Nos. 4,675,582; 4,825,111; 4,853,602; 5,036,262; 5,051,225; and 5,072,493. Although biaxially stretched films can be made by tubular blown film or flat film tenter stretching  
30 processes, it is preferable that the films of this invention, when used as tape backings, be

5 made by a flat film tenter stretching process to avoid thickness variations and processing difficulties typically associated with tubular blown film processes.

10 Flat film tenter stretching can be accomplished by sequential or simultaneous stretching processes. The simultaneous process surprisingly permits for the incorporation of greater levels of resin B which in turn impart more desirable properties including improved severability and clarity. An additional advantage of such a process is that the film surfaces do not contact stretching rollers as in the case of commercially available sequential film stretching lines, which preserves the film surface from defects caused by roller contact. In addition, other defects like thickness variability, die lip instabilities, 15 hardbands and the like are minimized in comparison to tubular or blown film stretching processes.

20 The polypropylene composition is selected to allow biaxial stretch to an area stretch ratio of at least 36:1. The polypropylene composition also preferably allows stretch to occur at a line speed of at least 30 meters/minute.

25 The biaxially oriented substrates 12 useful in this invention, when used as a backing 11 for a tape 10, preferably have a final thickness between about 0.002-0.005 cm. Variability in film thickness is preferably less than about 5%. Thicker and thinner films may be used, with the understanding that the film should be thick enough to avoid excessive flimsiness and difficulty in handling, while not being so thick so as to be 30 undesirably rigid or stiff and difficult to handle or use.

35 Backing 11 may optionally include additives and other components as is known in the art, preferably in an amount selected so as not to adversely affect the tensile and dispense properties attained by the preferred embodiments described herein. For example, the films of the present invention may contain fillers, plasticizers, colorants, lubricants, 40 processing aids, nucleating agents, ultraviolet-light stabilizing agents, and other additives. Typically such materials are added to a polymer before it is made into an oriented film (e.g., in the polymer melt before extrusion into a film). Organic fillers may include organic dyes and resins, as well as organic fibers such as nylon and polyimide fibers. 45 Inorganic fillers may include pigments, fumed silica, calcium carbonate, talc, diatomaceous earth, titanium dioxide, carbon fibers, carbon black, glass beads, glass 30 bubbles, mineral fibers, clay particles, metal particles and the like. Other additives such as

5 flame retardants, stabilizers, antioxidants, compatibilizers, antimicrobial agents (e.g., zinc  
oxide), electrical conductors, and thermal conductors (e.g., aluminum oxide, boron nitride,  
10 aluminum nitride, and nickel particles) can be blended into the polymer used to form the  
film.

5 The adhesive 18 may be any suitable adhesive as is known in the art. Preferred  
adhesives are those activatable by pressure, heat or combinations thereof. Suitable  
15 adhesives include those based on acrylate, rubber resin, epoxies, urethanes or  
combinations thereof. The adhesive 18 may be applied by solution, water-based or hot-  
melt coating methods. The adhesive may be applied in any desired amount, and typically  
10 is applied to provide a conventional dry coating weight between about 0.0015 to 0.005  
grams/cm<sup>2</sup>.  
20

The backing 11 may be optionally treated by exposure to flame or corona  
25 discharge or other surface treatments including chemical priming to improve adhesion of  
subsequent coating layers. In addition, the second surface 16 may be coated with optional  
15 low adhesion backsize materials 20 to restrict adhesion between the opposite surface  
adhesive layer 18 and the backing 11, thereby allowing for production of adhesive tape  
rolls capable of easy unwinding, as is well known in the adhesive coated tape-making art.

30 Such a tape 10 is particularly well-suited for light duty home and office use or for  
other uses like die-cut tapes or other die-cut substrates.

20 In one preferred embodiment, tape 10 is provided in the form of a spirally wound  
roll 22 wound up in direction R and optionally on a core 24 as illustrated in Figure 2.  
35 Such rolls can be provided on a table top or hand held dispenser 26 as illustrated in Figure  
3. The dispensers can include a metal cutting blade or plastic cutting blade. Preferred  
dispensers include those available as SCOTCH brand Cat. 15 or Cat. 40 tabletop tape  
40 25 dispenser equipped with metal cutting blades, SCOTCH brand Cat. 25 or Cat. H-125/126  
plastic two-piece plastic dispensers equipped with metal cutting blades, and SCOTCH  
brand Cat. 104 or Cat. 105 injection-molded polystyrene dispensers with plastic cutting  
45 blades, all available from Minnesota Mining and Manufacturing Company, St. Paul,  
Minnesota.

5 The details of converting film backings into tapes is well within the skill of those in the art, and need not be described in any greater detail herein. See, for example, U.S. Patent No. 4,451,533, "Dispensable Polypropylene Adhesive-Coated Tape," (Wong et al).

10 The operation of the present invention will be further described with regard to the following detailed examples. These examples are offered to further illustrate the various specific and preferred embodiments and techniques. It should be understood, however, that many variations and modifications may be made while remaining within the scope of the present invention.

### Test Methods

#### Tensile Properties:

#### ASTM D-882-95A, Tensile Properties of Thin Plastic Sheeting, Method A

15 The tensile elongation-at-break of backings was measured by the procedures described in ASTM D-882-95A, "Tensile Properties of Thin Plastic Sheeting," Method A. The backings were conditioned for 24 hours at 25° C and 50% relative humidity. The tests were performed using a tensile-testing machine commercially available as a Model 400/S, from MTS Systems Corporation, Eden Prairie, MN. Specimens for this test were 1.91 cm wide and 15 cm in length. An initial jaw separation of 10.2 cm and a crosshead speed of 30 cm/min were used. Specimens were tested for each sample in the reference direction of the film. Results are reported in Table 2 below. The elongation-to-break values are reported for the reference direction based on the initial gauge length of the sample. As used herein, including the claims, the term "tensile elongation to break" is used to describe results obtained by the just-described method.

#### Melt Flow Rate: ASTM D 1238-95, Flow Rates of Thermoplastics by Extrusion

#### Plastometer

25 The melt flow rate of the resins and backing samples were measured using the procedures described in ASTM D 1238-95, Flow Rates of Thermoplastics by Extrusion Plastometer, Procedure B, Condition 230/2.16. A Tinius-Olsen Extrusion Plastometer Model U-E-4-78, Willow Grove, PA., equipped with a mechanically actuated timer was used. A one-inch piston arm travel distance was used for all samples. Samples were

charged into the heated plastometer and the residence time prior to measurement was kept at  $7.0 \pm 0.5$  minutes. When films are tested, the film sample is rolled up and introduced into the apparatus.

Weight Average Molecular Weight (Mw):

ASTM D 5296-92, Molecular Weight Averages by Size Exclusion Chromatography (SEC)

The weight average molecular weights (Mw) were measured using ASTM D 5296-92, Molecular Weight Averages by Size Exclusion Chromatography (SEC). A Waters 150C chromatograph (Waters Corporation, Milford, Massachusetts) equipped with a two-column set (Jordi Associates mixed bed with 500 angstrom pore size) was used. Samples were in the form of pellet, cast sheet, or stretched film.

10.0 ml of 1,2,4-trichlorobenzene (TCB) containing 0.1% Ionol (antioxidant) and Phosphite 168 (high temperature stabilizer) were added to approximately 25 mg of sample and dissolved by heating at 160° C for 12.0 hrs. The solutions were then filtered using the internal filtration system (0.5 micrometer) of the Waters 150C instrument, and 150 microliters of each solution were injected into the chromatograph operating at a temperature of 140° C and an eluent (TCB) rate of 1.0 ml/min. Concentration changes were measured using an internal refractive index detector. The weight average molecular weights (Mw) were calculated using a Dell computer equipped with Polymer Labs PL Caliber software, based on a calibration made of narrow dispersity polystyrene standards ranging in Mw from  $6.30 \times 10^6$  to 800 grams/mole.

ASTM D 4065-95, Polydispersity Index by Measurement of Dynamic Mechanical Properties of Plastics

The polydispersity index of both polypropylene composition and film was measured according to ASTM D 4065-95, using a Rheometrics Dynamic Mechanical Spectrometer (Rheometrics Scientific Incorporated, Piscataway, New Jersey) oscillating disc rheometer. Sample film or resin was placed between two 25 mm diameter parallel plates with a gap of about 1-3 mm in an oven at 200°C, and subjected to an oscillatory strain sweep in the frequency range of 0.1 to 400 radians per second. The dynamic stress response was measured and values of the storage modulus G' and loss modulus G''



5 calculated. The point where these moduli have co-incident values is the crossover point, and the value of dynamic modulus at this point is  $G_c$ , in dyne/cm<sup>2</sup>. The polydispersity index is calculated as  $PI = 10^6/G_c$ .

10  
5 ASTM D 1003-95, Transmittance Haze

The transmittance haze of inventive film was measured using a Haze-guard Plus transmission and haze meter (BYK-Gardiner, Silver Springs, MD.) according to the procedure described in ASTM D 1003-95.

20  
10 Severance Properties: Dispense Testing of Films

Test specimens 1.91 cm wide and 15 cm long were slit from uncoated sample films using a razor blade cutter equipped with new blades. Test specimens were conditioned for 24 hours at 25° C and 50% relative humidity prior to testing.

25  
15 The test fixture used to measure severability is shown in Figure 4. The test fixture comprised a commercially available tape dispenser 100M (Scotch™ Cat. H-127 two-piece polystyrene molded dispenser equipped with a metal cutting blade, available as of the filing date hereof from Minnesota Mining & Manufacturing Co., St. Paul, MN) or  
30 commercially available tape dispenser 100P (Scotch™ Cat. 122 two-piece molded polystyrene dispenser equipped with a plastic cutting blade, available as of the filing date hereof from Minnesota Mining & Manufacturing Co., St. Paul, MN) mounted to a 15.2 cm  
35 x 15.2 cm x 1.1 cm aluminum rear mounting plate 102. The dispenser was restricted from flexing during the severing test by being placed between the rear mounting plate 102 and a 0.3 cm thick aluminum front mounting plate 104 milled to the contour of the test dispenser 100P or 100M. The test dispenser was firmly held in place between the front 104 and rear  
40 102 mounting plates by a threaded thumbscrew 106. The rear mounting plate 102 was affixed to a 2.4 cm diameter cylindrical base mounting stud 108 by machine screws 110. The base mounting stud 108 was milled to include a 90° angle cut-out so that the rear  
45 mounting plate 102 was held in the vertical centerline of the tensile testing machine, that is, the angle between the axis of the rear mounting plate 102 and test dispenser 100P or

100M was 0° with respect to the machine centerline. The base stud 108 was affixed to the testing machine deck by locking pins inserted into drillouts 109 in the base stud.

The test dispenser 100M or 100P was mounted onto the rear mounting plate 102 by inserting the dispenser hub over an aluminum hub mounting shaft 112 which is screwed into the rear mounting plate 102. The bottom of the dispenser rested against seat 115 which prevented rotation of the dispenser during testing. The test dispenser was mounted so that the row of teeth of the dispenser cutting blade was perpendicular to the machine centerline. In this way, the film being tested was loaded substantially uniformly across its width when severed.

Dispenser 100M included a steel serrated cutting blade 120 illustrated in Figures 5 and 6. Steel cutting blade 120 was formed of about 0.05 cm thick nickel plated steel and included a rectangular land portion 122 at least as wide as the film 12 and about 0.3 cm long in the direction corresponding to the reference direction R of the film 12 extending across the blade. The land portion 122 defines a generally planar surface to which the test sample is temporarily secured. Blade 120 also included a blade support portion 126 at the rear edge of the land portion 122, with the land portion forming an angle  $\beta$  of 80° with the support 126. Blade support 126 is about 1.32 cm long. Blade 120 further included a generally U-shaped portion 128 at the edge of the land portion opposite the support portion which has a row of teeth 130 along its distal edge. Each tooth 130 is generally triangular, has a tip in or slightly lower than the plane of the land 122 and spaced from the tips of adjacent teeth 130 by about 0.12 cm, is defined by a height of about 0.06 cm, a sharpness defined by a radius of curvature of about 0.003 cm, and the apex 132 of said teeth 130 form an included angle of 60°. The teeth 130 project outward from the plane of the blade support portion 126 at an angle  $\alpha$  of about 50°. The sides of the generally U-shaped portion 128 are at an angle  $\gamma$  to one another of 72°.

Dispenser 100P includes an injection-molded polystyrene blade 140 illustrated in Figures 7-9. Polystyrene blade 140 on dispenser 100P is integrally molded with one of the two halves of the tape dispenser 100P. Blade 140 is formed by filling the cavities of a steel mold using a typical injection molding process. As seen in Figures 8 and 9, blade 140 includes a land surface 144 which is about 0.35 cm wide. Land surface 144 is slightly convex, having a radius of curvature of 2.54 cm. Forward of land 144 is a V-shaped

5 portion formed by surfaces 148 and 149 which meet at an inside angle  $\delta$  of  $125^\circ$ . Surface  
148 of the V-groove makes an angle of  $\nu$  with the linear approximation of land 144 of  $70^\circ$ .  
A series of ridges 154 extend from the front of the dispenser. The ridges 154 are each  
10 formed by sides 154a and 154b which meet at ridge 154c. Each tooth peak 150 is formed  
5 by the intersection of surface 149 with the ridges 154. As best seen in Figures 7 and 9,  
each tooth is thereby formed by the intersection of three planes: sides 154a and 154b of  
ridge 154, and surface 149 of the V-shaped groove. As seen in Figure 9, sides 154a and  
15 154b meet at an included angle  $\theta$  of  $74^\circ$ . As seen in Figure 8, surface 149 forms an angle  
 $\phi$  of  $50^\circ$  with edge 154c of ridge 154. Each tooth 150 has a tip in or slightly lower than  
10 the plane of the land surface 144 and is spaced from the tips of adjacent teeth 150 by about  
0.127 cm. Each tooth has a height of about 0.020 cm, measured as the height H from the  
20 peak of the tooth to the adjoining valleys between teeth. Each tooth has an edge sharpness  
having a radius of curvature of about 0.010 cm.

25 In either test dispenser, a piece of double-coated adhesive tape (Scotch™ Cat. 665)  
15 was applied to land area 122 or 144 and the test specimen was adhered firmly to the  
adhesive surface of the double-coated tape with finger pressure to prevent forward motion  
during severance testing.

30 The test specimen was aligned at an angle of  $0^\circ$  to the machine centerline so that  
the force of the dispenser was substantially evenly distributed across the width of the  
20 sample. The dispenser 100M or 100P was oriented such that the tips of the cutting blade  
120 or 140 were directly under the jaws 162. For tests using the dispenser 100M with  
35 metal dispenser 120, the dispenser was oriented at an angle such that the land 122 was at  
an angle  $\sigma_1$  of  $110^\circ$  relative to the vertical direction of travel A of the tester (see Figure 10,  
which illustrates only the cutter blade 120 relative to the jaws 162, with the rest of the  
40 25 dispenser and test fixture removed for illustrative purposes only). For tests using the  
dispenser 100P with plastic blade 140, the dispenser was oriented at an angle such that the  
edge 154c of ridge 154 was at an angle  $\sigma_2$  of  $32^\circ$  relative to the vertical direction of travel  
A of the tester (see Figure 11, which illustrates only the cutter blade 140 relative to the  
45 jaws 162, with the rest of the dispenser and test fixture removed for illustrative purposes  
30 only).

5 The free end of the test specimen was then gripped in the upper jaws 162 of the  
tensile testing machine so that the distance between the upper jaws and the cutting blade  
120 or 140 was 10.2 cm. The specimen was loaded with no tension so that the cutting  
blade did not contact the specimen prior to the start of the test. The upper jaws were  
10 5 attached to the machine crosshead which traveled on support rails 14. The test specimen  
was next pre-loaded in tension to a value of 0.9 N to make contact with the cutting blade  
120 or 140. The backing 11 was then pulled in direction A by the jaws 162 at a rate of 30  
cm/minute. The load and elongation of the specimen were measured and recorded, and  
15 the energy to sever was calculated from the area under the load/elongation, as illustrated in  
10 Figure 12, and reported in Table 1. In Figure 12, the load is indicated along the vertical  
axis, with the elongation indicated on the horizontal axis. The load and elongation  
increase along portion 200 of the curve, until the peak load 202 is reached, where the  
elongation is indicated by 204. The load then decreases as the elongation continues along  
20 portion 206 of the curve. As reported herein, the energy is calculated for that portion of  
the curve from zero elongation to the elongation 204 at maximum load 202. It is believed  
25 that the teeth of the dispenser puncture the film at about the point of maximum load 202,  
at which time the load decreases as the punctures through the film propagate to complete  
severance.

30 As used herein, including the claims, the term "The Dispense Test - Metal Blade"  
20 refers to the just described test using dispenser 100M, and the term "The Dispense Test -  
Plastic Blade" refers to the just described test using dispenser 100P.

#### 35 Preparation of Examples

##### 40 25 Preparation of Resin Master Batches

Sample resin master batches with a weight composition of low melt flow resin A  
and high melt flow resin B of 50:50 were prepared for making the biaxially oriented  
45 substrate Examples as follows. First, 50 wt% of FINA 3374 isotactic polypropylene  
homopolymer resin was compounded with 50 wt% of each of the three following resins:  
30 FINA 3860 polypropylene (resulting in Master Batch X); FINA 3892 polypropylene

(resulting in Master Batch Y); or FINA 98035 polypropylene (resulting in Master Batch Z); all supplied by FINA Oil & Chemical Co., Dallas, TX. The polypropylene master batches were mixed by feeding the separate polypropylene resins into a 50-mm twin screw extruder using a K-Tron T-35 volumetric feeder. The extruder was a 50 mm 10:1 L/D co-rotating Baker-Perkins twin screw. A 5-hole stranding die was mounted on the extruder and the extrudate strands were fed into a water bath prior to pelletizing. The extruder was operated at a rate of 48.5 lbs./hour at a speed of 275 rpm and a die temperature of 232° C. The final weight composition and melt flow rate were obtained by addition of neat homopolymer resin to the master batch resin to achieve the desired weight percentages reported in Table 1 below.

**Table 1: Weight Ratios of Polypropylene Resins**

Example	Neat Isotactic PP Resins				Master Batch Resins		
	3374	3860	3982	98035	X	Y	Z
1	100	-	-	-	-	-	-
2	80	-	-	-	20	-	-
3	60	-	-	-	40	-	-
4	40	-	-	-	60	-	-
5	100	-	-	-	-	-	-
6	40	-	-	-	60	-	-
7	20	-	-	-	80	-	-
8	100	-	-	-	-	-	-
9	40	-	-	-	60	-	-
10	100	-	-	-	-	-	-
11	50	-	-	-	50	-	-
12	-	50	-	-	50	-	-
13	-	100	-	-	-	-	-
14	50	-	-	-	-	50	-
15	-	-	50	-	-	50	-
16	-	-	-	50	-	-	50

#### Examples 1-4

The appropriate resin mixture was fed into the feed hopper of a 4.45 cm single screw extruder manufactured from H.P.M (Mt. Gilead, OH) having an extruder barrel temperature adjusted to produce a stable homogeneous melt of about 250-260°C. The polypropylene melt was extruded through a 17.8 cm single manifold sheet die onto a rotating water cooled steel casting wheel which had about 50-60° C water circulating

5 through it. The cast sheet was next passed through a quenching water bath maintained at about 30°C to produce a cast sheet having a thickness of about 0.16 cm.

10 Sequentially biaxially oriented polypropylene biaxially oriented substrates were prepared by a process known as the sequential tenter process. The cast sheet was passed  
5 over a first series of heating rolls maintained internally from about 127°C to 136°C, and then stretched between two nipped drawing rolls rotating at different speeds to attain a first draw ratio of 5.0:1 in extrusion or casting direction. The uniaxially stretched sheet  
15 was then fed into a tenter oven with multiple heat zones having temperatures ranging from 158° to 175° C and stretched or oriented between two tenter rails in the direction  
10 perpendicular to the first stretching at a draw ratio of about 9:1. The resulting film had a thickness of about 0.003-0.0035 cm and was cooled in air and annealed on an annealing  
20 drum with an internal temperature of 120°C. The edges were subsequently razor slit and the film wound onto a master roll. The film was slit into useful sample widths using a razor blade cutter equipped with fresh blades.

#### 25 Examples 5-7

30 Simultaneously biaxially oriented polypropylene Examples 5-7 were prepared by a process known as the simultaneous tenter process. First, the appropriate resin mixture was extruded to produce a stable homogeneous melt having a melt temperature of about  
20 257°C. The polypropylene melt was cast onto a water cooled steel casting wheel rotating at about 10 meters per minute which had about 11° C water circulating through it. The  
35 cast sheet was next passed through a quenching water bath maintained at about 20°C to produce a cast sheet having a thickness of about 0.15-0.2 cm.

40 The cast film was simultaneous stretched in longitudinal and transverse directions  
25 using a diverging spindle simultaneous biaxial orienting tenter equipped with 7:1 stretching spindles, at a line speed of 80-85 meters per minute and a stretching temperature of about 175-180° C to a final balanced area stretching ratio of about 50:1.

Examples 8-16

Examples 8-16 were cast as described above in Examples 1-4.

Examples 8-9 were simultaneously stretched in two perpendicular directions using a laboratory two-way film stretching machine known as a frame or batch stretcher as follows. The cast film sheet of 0.16 cm thickness was cut into square tablets of 6.83 cm on a side and held in the stretching oven of the batch stretcher by edgewise gripping with a series of clips to leave a stretchable sample of 5.08 cm on a side. The tablet was pre-heated for 90 seconds at 155° C, and stretched at a rate of about 300%/second in the reference direction and about 250%/second in the direction perpendicular to the first direction to a final area stretch ratio of about 40:1. Samples were immediately removed from the stretching machine to cool. The film had a nominal thickness of about 0.030 cm. The film was slit into useful sample widths using a razor blade cutter equipped with fresh blades.

Examples 10-16 were prepared by stretching the cast sheet described above simultaneously in two perpendicular directions using a laboratory two-way film stretching machine known as a frame or batch stretcher as follows. The cast film sheet of 0.16 cm thickness was cut into square tablets of 6.83 cm on a side and held in the stretching oven of the batch stretcher by edgewise gripping with a series of clips to leave a stretchable sample of 5.08 cm on a side. The tablet was pre-heated for 90 seconds at 155° C, then simultaneously stretched at a rate of about 300%/sec in the reference direction and about 300%/sec in the direction perpendicular to the reference direction to a final area stretch ratio of 50:1. The film was slit into useful sample widths using a razor blade cutter equipped with fresh blades.

Samples prepared in accordance with Examples 1-10, 12-13, and 15-16 were tested for severability by the Dispense Test - Metal Blade. Samples prepared in accordance with Examples 5, 7, and 10-15 were tested for severability by the Dispense Test - Plastic Blade. Samples from each Example were also tested for melt flow rate and weight average molecular weight  $M_w$  by the methods described above. Samples from each Example were also tested for tensile elongation at break by the method described above.

Table 2: Test Results

Ex.	MFR <sup>1</sup>	Mw <sup>2</sup>	PI <sup>3</sup>	Test <sup>4</sup>	Peak <sup>5</sup>	Energy <sup>6</sup>	Tensile Elong. <sup>7</sup>	Dispense Elong. <sup>8</sup>	Haze <sup>9</sup>
1	4.4	420		M	19.5	600	190	3.18	1.06
2	5.4	490		M	19.1	561	188	2.97	0.91
3	8.0	420		M	14.1	241	167	1.80	0.07
4	11.2	350		M	13.2	235	167	1.86	0.47
5	5.8			M	22.4	740	98	3.70	4.56
6				M	16.9	270	109	1.88	3.30
7	12.5			M	16.1	244	121	1.82	
8	7.5			M	14.6	310	70	1.77	1.23
9	19.6			M	12.8	249	55	1.56	0.79
10	3.2	418	3.4	M	23.8	634	87	2.89	
12	54.0	231	4.9	M	14.3	277	97	1.86	
13	100.0	183	6.5	M	14.5	269	103	1.71	
15	49.0		6.7	M	17.0	285	90	1.86	
16	45.0	224	4.9	M	15.5	248	86	1.72	
5	5.8	197		P	29.8	937	98	3.20	4.56
7	12.5	132		P	26.7	591	121	2.49	3.30
10	3.2	418	3.4	P	43.1	3370	87	7.31	
11	6.7	320	4.1	P	38.3	2920	93	6.82	
12	54.0	231	4.9	P	20.8	532	97	1.86	
13	100.0	183	6.5	P	17.2	286	103	1.71	
14	6.9	249	4.9	P	34.2	1895	85	5.05	
15	49.0		6.7	P	23.1	645	90	2.61	

1: Melt flow rate reported in grams/10 minutes measured according to ASTM D 1238-95, Flow Rates of Thermoplastics by Extrusion Plastometer, Procedure B, Condition 230/2.16.

2: The weight average molecular weights (Mw) reported in 1000 grams/mole were measured using ASTM D 5296-92, Molecular Weight Averages by Size Exclusion Chromatography (SEC).

3: PI: Polydispersity Index =  $10^6/G_c$  where  $G_c$  = rheometer crossover modulus value (dyne/cm<sup>2</sup>).

4: M = Dispense Test - Metal Blade; P = Dispense Test - Plastic Blade.

5: Peak load measured during Dispense Test, reported as (N/19.1 mm).

6: Energy to dispense measured by Dispense Test - Metal Blade, and/or Dispense Test - Plastic Blade, and reported as N-cm/cm<sup>2</sup>.

7: Tensile elongation-at-break was measured by the procedures described in ASTM D-882-95A, "Tensile Properties of Thin Plastic Sheeting," Method A and is reported in percent.

8: Elongation measured during Dispense Test - Metal Blade, and/or Dispense Test - Plastic Blade, reported in percent.



5 9: Measured by ASTM D1003-95 and reported in percent.

10 The tests and test results described above are intended solely to be illustrative, rather than predictive, and variations in the testing procedure can be expected to yield different results.

5 The present invention has now been described with reference to several embodiments thereof. The foregoing detailed description and examples have been given for clarity of understanding only. No unnecessary limitations are to be understood  
15 therefrom. The disclosures of all patents and patent applications cited herein are hereby incorporated by reference. It will be apparent to those skilled in the art that many changes  
10 can be made in the embodiments described without departing from the scope of the invention. Thus, the scope of the present invention should not be limited to the exact  
20 details and structures described herein, but rather by the structures described by the language of the claims, and the equivalents of those structures.

## Claims

5

10

15

20

25

30

35

40

45

50

55

**WHAT IS CLAIMED IS:**

1. An adhesive tape comprising:

a backing and a layer of adhesive on said backing;

wherein said backing has an energy to sever of up to 700 N-cm/cm<sup>2</sup> when severed according to The Dispense Test - Plastic Blade; and

wherein said backing comprises a biaxially oriented substrate, wherein said biaxially oriented substrate comprises an isotactic polypropylene composition, and wherein said biaxially oriented substrate has a melt flow rate of at least 8.

2. The adhesive tape of claim 1, wherein said biaxially oriented substrate comprises a monolayer substrate.

3. The adhesive tape of claim 1, wherein said biaxially oriented substrate comprises a multilayer film, and wherein with respect to the total thickness of said biaxially oriented substrate, at least 50% of the thickness of said biaxially oriented substrate comprises at least 90% isotactic polypropylene.

4. The adhesive tape of claim 3, wherein a first plurality of said layers each comprise at least 90% isotactic polypropylene, and wherein said first plurality of layers comprise at least 50% of the total thickness of said biaxially oriented substrate.

5. The adhesive tape of claim 1, wherein said biaxially oriented substrate has a weight average molecular weight of at least 100,000 grams/mole.

6. The adhesive tape of claim 1, wherein said backing has an elongation of up to 4% when severed according to The Dispense Test - Plastic Blade.

7. The adhesive tape of claim 1, wherein said backing has an energy to sever of up to 350 N-cm/cm<sup>2</sup> when severed according to The Dispense Test - Metal Blade.

8. The adhesive tape of claim 7, wherein said backing has an elongation of up to 4% when severed according to The Dispense Test - Metal Blade.

9. The adhesive tape of claim 1, wherein said backing has a tensile elongation to break of from 40% to 170%.

5                   10. The adhesive tape of claim 1, wherein said biaxially oriented substrate has a melt flow rate of at least 12.

10                   11. The adhesive tape of claim 10, wherein said biaxially oriented substrate has a melt flow rate of at least 20.

5                   12. The adhesive tape of claim 1, wherein said biaxially oriented substrate has a melt flow rate of from 8 to 100.

15                   13. The adhesive tape of claim 1, wherein said polypropylene composition has a weight average molecular weight of at least 100,000 grams per mole.

10                   14. The adhesive tape of claim 1, wherein said polypropylene composition has an isotacticity greater than about 90%.

20                   15. The adhesive tape of claim 1, wherein said polypropylene composition has a melt flow rate of at least 8.

25                   16. The adhesive tape of claim 15, wherein said polypropylene composition has a melt flow rate of at least 12.

15                   17. The adhesive tape of claim 16, wherein said polypropylene composition has a melt flow rate of at least 20.

30                   18. The adhesive tape of claim 15, wherein said polypropylene composition has a melt flow rate of from 8 to 100.

35                   19. The adhesive tape of claim 1, wherein said polypropylene composition comprises a blend of a first isotactic polypropylene having a first melt flow rate and a second isotactic polypropylene having a second melt flow rate greater than said first melt flow rate.

40                   20. The adhesive tape of claim 19, wherein said first melt flow rate is about 0.5 - 8.0 and wherein said second melt flow rate is at least 8.0.

25                   21. The adhesive tape of claim 20, wherein said second melt flow rate is at least 50.

45                   22. The adhesive tape of claim 20, wherein said second melt flow rate is up to about 150.

5                   23. The adhesive tape of claim 22, wherein said first melt flow rate is about 0.5 to 5.

10                   24. The adhesive tape of claim 19, wherein said first polypropylene has a weight average molecular weight of at least 350,000 and said second polypropylene has a weight average molecular weight of at least 100,000.

15                   25. The adhesive tape of claim 1, wherein said biaxially oriented substrate has been oriented to a final area stretch ratio of at least 36:1.

20                   26. The adhesive tape of claim 25, wherein said biaxially oriented substrate has been simultaneously biaxially oriented.

25                   27. The adhesive tape of claim 25, wherein said biaxially oriented substrate has been sequentially biaxially oriented.

30                   28. The adhesive tape of claim 1, wherein said adhesive comprises a pressure sensitive adhesive

35                   29. The adhesive tape of claim 28, wherein said adhesive tape is spirally wound so as to provide a roll of tape.

40                   30. The adhesive tape of claim 29, wherein said roll is mounted on a dispenser including a metal cutting blade.

45                   31. The adhesive tape of claim 29, wherein said roll is mounted on a dispenser including a plastic cutting blade.

50                   32. An assembly of a roll of pressure sensitive adhesive tape mounted on a dispenser, the assembly comprising:

                    a) a roll of pressure sensitive adhesive tape, said tape comprising a backing and a layer of pressure sensitive adhesive on said backing;

                    i) wherein said backing has an energy to sever of up to 700 N-cm/cm<sup>2</sup> when severed according to The Dispense Test - Plastic Blade;

                    ii) wherein said backing has an elongation of up to 4% when severed according to The Dispense Test - Plastic Blade;

                    iii) wherein said backing has an elongation to break of from 40% to 170%; and

iv) wherein said backing comprises a biaxially oriented substrate, wherein said biaxially oriented substrate comprises an isotactic polypropylene composition having an isotacticity of at least 90%, and wherein said biaxially oriented substrate has a melt flow rate of at least 20; and

b) a dispenser, said dispenser including a roll mount having said roll of tape rotatably mounted thereon, and a plastic serrated cutting blade for severing said adhesive tape.

33. The assembly of claim 32, wherein said biaxially oriented substrate comprises a monolayer substrate.

34. An adhesive tape comprising:

a backing and a layer of adhesive on said backing;

wherein said backing has an energy to sever of up to 350 N-cm/cm<sup>2</sup> when severed according to The Dispense Test - Metal Blade; and

wherein said backing comprises a biaxially oriented substrate, wherein said biaxially oriented substrate comprises an isotactic polypropylene composition, and wherein said biaxially oriented substrate has a melt flow rate of at least 8.

35. The adhesive tape of claim 34, wherein said biaxially oriented substrate comprises a monolayer substrate.

36. The adhesive tape of claim 34, wherein said biaxially oriented substrate comprises a multilayer film, and wherein with respect to the total thickness of said biaxially oriented substrate, at least 50% of the thickness of said biaxially oriented substrate comprises at least 90% isotactic polypropylene.

37. The adhesive tape of claim 36, wherein a first plurality of said layers each comprise at least 90% isotactic polypropylene, and wherein said first plurality of layers comprise at least 50% of the total thickness of said biaxially oriented substrate.

38. The adhesive tape of claim 34, wherein said biaxially oriented substrate has a weight average molecular weight of at least 100,000 grams/mole.

39. The adhesive tape of claim 34, wherein said backing has an elongation of up to 4% when severed according to The Dispense Test - Metal Blade.

5                   40. The adhesive tape of claim 34, wherein said backing has a tensile elongation to break of from 40% to 170%.

10                   41. The adhesive tape of claim 34, wherein said biaxially oriented substrate has a melt flow rate of at least 12.

5                   42. The adhesive tape of claim 41, wherein said biaxially oriented substrate has a melt flow rate of at least 20.

15                   43. The adhesive tape of claim 34, wherein said biaxially oriented substrate has a melt flow rate of from 8 to 100.

10                   44. The adhesive tape of claim 34, wherein said polypropylene composition has an isotacticity greater than about 90%.

20                   45. The adhesive tape of claim 34, wherein said polypropylene composition has a melt flow rate of at least 8.

25                   46. The adhesive tape of claim 45, wherein said polypropylene composition has a melt flow rate of at least 12.

15                   47. The adhesive tape of claim 46, wherein said polypropylene composition has a melt flow rate of at least 20.

30                   48. The adhesive tape of claim 45, wherein said polypropylene composition has a melt flow rate of from 8 to 100.

35                   49. The adhesive tape of claim 34, wherein said polypropylene composition comprises a blend of a first isotactic polypropylene having a first melt flow rate and a second isotactic polypropylene having a second melt flow rate greater than said first melt flow rate.

40                   50. The adhesive tape of claim 49, wherein said first melt flow rate is about 0.5 - 8.0 and wherein said second melt flow rate is at least 8.0.

25                   51. The adhesive tape of claim 50, wherein said second melt flow rate is at least 50.

45                   52. The adhesive tape of claim 50, wherein said second melt flow rate is up to about 150.

5 53. The adhesive tape of claim 51, wherein said first melt flow rate is about 0.5 to 5.

10 54. The adhesive tape of claim 49, wherein said first polypropylene has a weight average molecular weight of at least 350,000 and said second polypropylene has a weight  
5 average molecular weight of at least 100,000.

15 55. The adhesive tape of claim 34, wherein said biaxially oriented substrate has been oriented to a final area stretch ratio of at least 36:1.

56. The adhesive tape of claim 55, wherein said biaxially oriented substrate has been simultaneously biaxially oriented.

20 57. The adhesive tape of claim 55, wherein said biaxially oriented substrate has been sequentially biaxially oriented.

58. The adhesive tape of claim 34, wherein said adhesive comprises a pressure sensitive adhesive.

25 59. The adhesive tape of claim 58, wherein said adhesive tape is spirally wound so  
15 as to provide a roll of tape.

30 60. The adhesive tape of claim 59, wherein said roll is mounted on a dispenser including a metal cutting blade.

61. The adhesive tape of claim 59, wherein said roll is mounted on a dispenser including a plastic cutting blade.

35 62. An adhesive tape backing comprising a biaxially oriented substrate, wherein said biaxially oriented substrate comprises an isotactic polypropylene composition, wherein said biaxially oriented substrate has a melt flow rate of at least 8, and wherein said backing has an energy to sever of up to 700 N-cm/cm<sup>2</sup> when severed according to The  
40 Dispense Test - Plastic Blade.

25 63. The adhesive tape backing of claim 62, wherein said biaxially oriented substrate comprises a monolayer substrate.

45 64. The adhesive tape backing of claim 62, wherein said biaxially oriented substrate comprises a multilayer film, and wherein with respect to the total thickness of said biaxially oriented substrate, at least 50% of the thickness of said biaxially oriented  
30 substrate comprises at least 90% isotactic polypropylene.



5                   65. The adhesive tape backing of claim 64, wherein a first plurality of said layers each comprise at least 90% isotactic polypropylene, and wherein said first plurality of layers comprise at least 50% of the total thickness of said biaxially oriented substrate.

10                   66. The adhesive tape backing of claim 62, wherein said biaxially oriented  
5 substrate has a weight average molecular weight of at least 100,000 grams/mole.

15                   67. The adhesive tape backing of claim 62, wherein said backing has an elongation of up to 4% when severed according to The Dispense Test - Plastic Blade.

15                   68. The adhesive tape backing of claim 62, wherein said backing has a tensile elongation to break of from 40% to 170%.

20                   69. The adhesive tape backing of claim 62, wherein said biaxially oriented  
20 substrate has a melt flow rate of at least 12.

25                   70. The adhesive tape backing of claim 69, wherein said biaxially oriented substrate has a melt flow rate of at least 20.

25                   71. The adhesive tape backing of claim 62, wherein said biaxially oriented  
15 substrate has a melt flow rate of from 8 to 100.

30                   72. The adhesive tape backing of claim 62, wherein said polypropylene composition has a weight average molecular weight of at least 100,000 grams per mole.

35                   73. The adhesive tape backing of claim 62, wherein said polypropylene composition has an isotacticity greater than about 90%.

35                   74. The adhesive tape backing of claim 62, wherein said polypropylene  
20 composition has a melt flow rate of at least 8.

40                   75. The adhesive tape backing of claim 74, wherein said polypropylene composition has melt flow rate of at least 12.

45                   76. The adhesive tape backing of claim 75, wherein said polypropylene  
25 composition has a melt flow rate of at least 20.

45                   77. The adhesive tape backing of claim 74, wherein said polypropylene composition has a melt flow rate of from 8 to 100.

5                   78. The adhesive tape backing of claim 62, wherein said polypropylene composition comprises a blend of a first isotactic polypropylene having a first melt flow rate and a second isotactic polypropylene having a second melt flow rate greater than said first melt flow rate.

10                   5                   79. The adhesive tape backing of claim 78, wherein said first melt flow rate is about 0.5 - 8.0 and wherein said second melt flow rate is at least 8.0.

15                   80. The adhesive tape backing of claim 79, wherein said second melt flow rate is at least 50.

20                   81. The adhesive tape backing of claim 79, wherein said second melt flow rate is up to about 150.

25                   82. The adhesive tape backing of claim 81, wherein said first melt flow rate is about 0.5 to 5.

30                   83. The adhesive tape backing of claim 78, wherein said first polypropylene has a weight average molecular weight of at least 350,000 and said second polypropylene has a weight average molecular weight of at least 100,000.

35                   84. The adhesive tape backing of claim 62, wherein said biaxially oriented substrate has been oriented to a final area stretch ratio of at least 36:1.

40                   85. The adhesive tape backing of claim 84, wherein said biaxially oriented substrate has been simultaneously biaxially oriented.

45                   20                   86. The adhesive tape backing of claim 84, wherein said biaxially oriented substrate has been sequentially biaxially oriented.

50                   87. The adhesive tape backing of claim 62, further comprising a layer of adhesive on said backing.

55                   88. The adhesive tape backing of claims 87, wherein said adhesive comprises a pressure sensitive adhesive.

                  89. The adhesive tape backing of claim 88, wherein said adhesive tape is spirally wound so as to provide a roll of tape.

                  90. The adhesive tape backing of claim 89, wherein said roll is mounted on a dispenser including a metal cutting blade.

5

91. The adhesive tape backing of claim 89, wherein said roll is mounted on a dispenser including a plastic cutting blade.

10

15

20

25

30


35

40


45

50


55




*Fig. 1*




*Fig. 2*




*Fig. 3*


**Fig. 4**




**Fig. 5**




**Fig. 6**





**Fig. 7**




**Fig. 8**



**Fig. 9**

**Fig. 10****Fig. 11**



***Fig. 12***

## INTERNATIONAL SEARCH REPORT

Int. Appl. No.

PCT/US 98/24105

A. CLASSIFICATION OF SUBJECT MATTER  
 IPC 6 C09J/02 C08J5/18 B32B27/32

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
 IPC 6 C09J C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Section Ch, Week 9329 Derwent Publications Ltd., London, GB: Class A17, AN 93-231949 XP002107479 & JP 05 154905 A (TORAY IND INC) , 22 June 1993  see abstract	1,2, 5-18,25, 27,34, 35, 38-48, 55,57, 62,63, 66-77, 84,86,87
X	US 3 324 218 A (HORST GEBLER ET AL) 6 June 1967 cited in the application see column 1, line 56 - line 67 see column 2, line 26 - line 28; example see claims; figure 1  --- -/--	62,63, 66-77, 84,86,87

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"S" document member of the same patent family

Date of the actual completion of the international search

28 June 1999

Date of mailing of the international search report

07/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3016

Authorized officer

De Jonge, S

# INTERNATIONAL SEARCH REPORT

Int. Patent Application No.  
PCT/US 98/24105

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 459 059 A (MINNESOTA MINING & MFG) 4 December 1991 see page 4, line 29 - line 35 see claims; figures 1-3 ---	1-91
A	US 4 451 533 A (WONG ROY ET AL) 29 May 1984 cited in the application see column 2, line 59 - column 3, line 7; claims; examples 1,5,6,8 ---	1-91
A	US 3 887 745 A (YOSHII TOSHIYA ET AL) 3 June 1975 cited in the application see column 3, line 34 - line 43; claim 1 -----	1-91

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Patent Application No

PCT/US 98/24105

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3324218 A	06-06-1967	NONE	
EP 0459059 A	04-12-1991	AU 629101 B AU 7104991 A CA 2036671 A DE 69011097 D DE 69011097 T MX 173296 B	24-09-1992 07-11-1991 06-09-1991 01-09-1994 26-01-1995 14-02-1994
US 4451533 A	29-05-1984	AU 567715 B AU 2427084 A BR 8400542 A CA 1217392 A EP 0116457 A JP 2097277 C JP 6051865 B JP 59152976 A MX 170507 B	03-12-1987 16-08-1984 11-09-1984 03-02-1987 22-08-1984 02-10-1996 06-07-1994 31-08-1984 26-08-1993
US 3887745 A	03-06-1975	JP 49045950 A JP 50037054 B DE 2339892 A GB 1416357 A	02-05-1974 29-11-1975 04-04-1974 03-12-1975

# INTERNATIONAL SEARCH REPORT

Int. Patent Application No.  
PCT/US 98/24105

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 459 059 A (MINNESOTA MINING & MFG) 4 December 1991 see page 4, line 29 - line 35 see claims; figures 1-3 ---	1-91
A	US 4 451 533 A (WONG ROY ET AL) 29 May 1984 cited in the application see column 2, line 59 - column 3, line 7; claims; examples 1,5,6,8 ---	1-91
A	US 3 887 745 A (YOSHII TOSHIYA ET AL) 3 June 1975 cited in the application see column 3, line 34 - line 43; claim 1 -----	1-91

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. dional Application No

PCT/US 98/24105

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3324218 A	06-06-1967	NONE	
EP 0459059 A	04-12-1991	AU 629101 B AU 7104991 A CA 2036671 A DE 69011097 D DE 69011097 T MX 173296 B	24-09-1992 07-11-1991 06-09-1991 01-09-1994 26-01-1995 14-02-1994
US 4451533 A	29-05-1984	AU 567715 B AU 2427084 A BR 8400542 A CA 1217392 A EP 0116457 A JP 2097277 C JP 6051865 B JP 59152976 A MX 170507 B	03-12-1987 16-08-1984 11-09-1984 03-02-1987 22-08-1984 02-10-1996 06-07-1994 31-08-1984 26-08-1993
US 3887745 A	03-06-1975	JP 49045950 A JP 50037054 B DE 2339892 A GB 1416357 A	02-05-1974 29-11-1975 04-04-1974 03-12-1975